



CONCRETE SIDEWALK SECTION DETAIL

**NOTES:**

1. SIDEWALK JOINTS SHALL BE IN ACCORDANCE WITH FDOT STANDARDS FOR ROAD CONSTRUCTION, (latest edition), TOPIC # 625-010-003, INDEX 522-001.
2. SIDEWALK TRUE MEASURE DEPTH THROUGH DRIVES/ENTRANCES SHALL BE:  
 6-0" FOR RESIDENTIAL DRIVEWAYS.  
 7-1/4" FOR COMMERCIAL TURNOUTS AND MULTIFAMILY TURNOUTS  
 7-1/4" FOR INDUSTRIAL TURNOUTS.
3. CONCRETE STRENGTH SHALL BE 3000 PSI MINIMUM AND SHALL HAVE A MINIMUM 470 LB/CY OF PORTLAND CEMENT AND A MAXIMUM WATER TO CEMENT RATIO OF 0.53 LBS/LB.
4. CLEAR ZONE AS DEFINED IN FDOT "FLORIDA GREENBOOK".
5. SIDEWALK EDGE TO MATCH ROAD CROWN ELEVATION TO EXTENT PRACTICAL.
6. MINIMUM SIDEWALK THICKNESS SHALL BE 5-1/2 INCHES.



**TOWN OF JUPITER**  
**ENGINEERING DIVISION**  
 210 MILITARY TRAIL  
 JUPITER, FLORIDA 33458  
 (561) 746-5134

**Concrete Sidewalk**  
 DETAIL AND REQUIREMENTS

V:\Engineering\Drawings\Details\2025\109a - Sidewalk - Concrete FM.dwg

DETAIL NUMBER  
**109a**  
 Revised 202111